

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 400 610 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
24.03.2004 Bulletin 2004/13

(51) Int Cl.7: **C23C 30/00, C23C 16/00,
C23C 14/22, C23C 14/08**

(21) Application number: **03255192.1**

(22) Date of filing: **21.08.2003**

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IT LI LU MC NL PT RO SE SI SK TR**
Designated Extension States:
AL LT LV MK

(30) Priority: **21.08.2002 US 226108
12.08.2003 US 641585**

(71) Applicant: **UNITED TECHNOLOGIES
CORPORATION**
Hartford, CT 06101 (US)

(72) Inventors:
• **Litton, David A.**
Rocky Hill, CT 06067 (US)

• **Trubelja, Mladen F.**
Manchester, CT 06040 (US)
• **Ullon, Nicholas E.**
Marlborough, CT 06447 (US)
• **Maloney, Michael J.**
Marlborough, CT 06447 (US)
• **Warrler, Sunil Govinda**
Middletown, CT 06457 (US)

(74) Representative: **Hall, Matthew Benjamin
Frank B. Dehn & Co.**
179 Queen Victoria Street
London EC4V 4EL (GB)

(54) **Thermal barrier coatings with low thermal conductivity comprising lanthanide sesquioxides**

(57) A ceramic material having particular utility as a thermal insulating or thermal barrier coating on metallic substrates is provided. The ceramic material broadly comprises at least one oxide and the balance comprising a first oxide selected from the group consisting of zirconia, ceria, and hafnia. The at least one has a for-

mula A_2O_3 where A is selected from the group consisting of La, Pr, Nd, Sm, Eu, Tb, In, Sc, Y, Dy, Ho, Er, Tm, Yb, Lu, and mixtures thereof. The present invention also broadly relates to an article having a metal substrate and a thermal barrier coating as discussed above.

EP 1 400 610 A1

Description

[0001] This invention relates to thermal barrier coatings made from ceramic materials and to metallic parts having such thermal barrier coatings. The thermal barrier coatings have particular utility in gas turbine engines.

[0002] Gas turbine engines are well developed mechanisms for converting chemical potential energy, in the form of fuel, to thermal energy and then to mechanical energy for use in propelling aircraft, generating electrical power, pumping fluids, etc. At this time, the major available avenue for improved efficiency of gas turbine engines appears to be the use of higher operating temperatures. However, the metallic materials used in gas turbine engines are currently very near the upper limits of their thermal stability. In the hottest portion of modern gas turbine engines, metallic materials are used at gas temperatures above their melting points. They survive because they are air cooled. But providing air cooling reduces engine efficiency.

[0003] Accordingly, there has been extensive development of thermal barrier coatings for use with cooled gas turbine aircraft hardware. By using a thermal barrier coating, the amount of cooling air required can be substantially reduced, thus providing a corresponding increase in efficiency.

[0004] Such coatings are invariably based on ceramic. Mullite and alumina have been proposed, but zirconia is the current material of choice. Zirconia must be modified with a stabilizer to prevent the formation of the monoclinic phase. Typical stabilizers include yttria, calcia, ceria, and magnesia.

[0005] Generally speaking, metallic materials have coefficients of thermal expansion which exceed those of ceramic materials. Consequently, one of the problems that must be addressed in the development of successful thermal barrier coatings is to match the coefficient of thermal expansion of the ceramic material to the metallic substrate so that upon heating, when the substrate expands, the ceramic coating material does not crack. Zirconia has a high coefficient of thermal expansion and this is a primary reason for the success of zirconia as a thermal barrier material on metallic substrates.

[0006] Despite the success with thermal barrier coatings, there is a continuing desire for improved coatings which exhibit superior thermal insulation capabilities, especially those improved in insulation capabilities when normalized for coating density. Weight is always a critical factor when designing gas turbine engines, particularly rotating parts. Ceramic thermal barrier coatings are not load supporting materials, and consequently they add weight without increasing strength. There is a strong desire for a ceramic thermal barrier material which adds the minimum weight while providing the maximum thermal insulation capability. In addition, there are the normal desires for long life, stability and

economy.

[0007] Accordingly, it is an object of the present invention to provide thermal barrier coatings having low thermal conductivity

5 [0008] It is a further object of the present invention to provide thermal barrier coatings as above which have utility in gas turbine engines.

[0009] The foregoing objects are attained by the thermal barrier coatings of the present invention.

10 [0010] In accordance with a first embodiment of the present invention, a thermal barrier coating is provided which broadly comprises at least 15 mol% of at least one lanthanide sesquioxide and the balance comprising a first oxide selected from the group consisting of zirconia, ceria, and hafnia. The first oxide is preferably present in an amount greater than 50 mol%. The at least one lanthanide sesquioxide has a formula A_2O_3 where A is selected from the group consisting of La, Pr, Nd, Sm, Eu, Tb, and mixtures thereof.

20 [0011] Other embodiments of thermal barrier coating in accordance with the present invention include the following.

[0012] In a second embodiment of the present invention, a thermal barrier coating is provided which broadly comprises an oxide present in an amount from 5 to 60 mol% with the oxide having a formula A_2O_3 where A is selected from the group consisting of In, Sc, Y, Dy, Ho, Er, Tm, Yb, Lu, and mixtures thereof, and the balance comprising a first oxide selected from the group consisting of zirconia, hafnia, and ceria.

30 [0013] In a third embodiment of the present invention, a thermal barrier coating is provided which broadly comprises a lanthanide sesquioxide and the balance comprising a first oxide selected from the group consisting of zirconia, hafnia, and ceria. The lanthanide sesquioxide is present in an amount sufficient to create more than one oxygen vacancy on average adjacent each zirconium, hafnium, and cerium ion.

35 [0014] In a fourth embodiment of the present invention, a thermal barrier coating is provided which broadly comprises from 15 to 60 mol% of a lanthanide sesquioxide having a formula A_2O_3 where A is selected from the group consisting of Er, Nd, Yb, Eu, Dy, Pr, Sm, and La, and the balance zirconia.

40 [0015] In a fifth embodiment of the present invention, a thermal barrier coating is provided which broadly comprises at least 15 mol% yttria, and a lanthanide sesquioxide having a formula A_2O_3 with A being selected from the group of Er, Nd, Yb, Eu, Dy, Gd, and Pr, and the balance zirconia.

45 [0016] In a sixth embodiment of the present invention, a thermal barrier coating is provided which broadly comprises from 9 to 15 mol% Yb_2O_3 , and from 1.0 to 48 mol% of a lanthanide sesquioxide having a formula A_2O_3 where A is selected from the group consisting of Er, Nd, Eu, Dy, Gd, and Pr, and the balance zirconia.

55 [0017] In a seventh embodiment of the present invention, a thermal barrier coating is provided which broadly

comprises greater than 15 mol% Yb_2O_3 , and a lanthanide sesquioxide having a formula A_2O_3 where A is selected from the group consisting of Er, Nd, Eu, Dy, Gd, and Pr, and the balance zirconia.

[0018] In an eighth embodiment of the present invention, a thermal barrier coating is provided which broadly comprises from 20 to 30 mol% Sc_2O_3 , and a lanthanide sesquioxide having a formula A_2O_3 where A is selected from the group consisting of Er, Nd, Eu, Dy, Gd, and Pr, and the balance zirconia.

[0019] In a ninth embodiment of the present invention, a thermal barrier coating is provided which broadly comprises greater than 30 mol% Sc_2O_3 , a lanthanide sesquioxide having a formula A_2O_3 where A is selected from the group consisting of Nd, Eu, Dy, Gd, Er, and Pr, and the balance zirconia.

[0020] In a tenth embodiment of the present invention, a thermal barrier coating is provided which broadly comprises from 11 to 20 mol% In_2O_3 , and a lanthanide sesquioxide having a formula A_2O_3 where A is selected from the group consisting of Er, Nd, Eu, Dy, Gd, and Pr, and the balance zirconia.

[0021] In an eleventh embodiment of the present invention, a thermal barrier coating is provided which broadly comprises more than 20 mol% In_2O_3 , and a lanthanide sesquioxide having a formula A_2O_3 where A is selected from the group consisting of Er, Nd, Eu, Dy, Gd, and Pr, and the balance zirconia.

[0022] In a twelfth embodiment of the present invention, a thermal barrier coating is provided which broadly comprises from 5 to 60 mol% of at least one of La_2O_3 and Sm_2O_3 , and from 5 to 60 mol% of at least one oxide having a formula A_2O_3 where A is selected from the group consisting of Sc, In, Y, Pr, Nd, Eu, Sm, Gd, Dy, Er, and Yb, and the balance zirconia.

[0023] Other embodiments of thermal barrier coatings in accordance with the present invention are included herein.

[0024] The present invention also relates to an article which broadly comprises a metal substrate and one of the above thermal barrier coatings. The article may have a bond coat intermediate the metal substrate and the thermal barrier coating.

[0025] Other details of preferred thermal barrier coatings of the present invention, as well as other objects and advantages attendant thereto, are set forth in the following detailed description which is given by way of example only.

[0026] The essence of the present invention arises from the discovery that certain ceramic materials have great utility as thermal barrier coatings on metallic substrates, particularly those used to form components, such as the airfoils, of turbine engine components. These ceramic materials have such utility because they exhibit lower thermal conductivity than conventional thermal barrier coatings such as 7 weight% yttria stabilized zirconia.

[0027] In accordance with the present invention, a first

embodiment of a thermal barrier coating which exhibits such a lower thermal conductivity comprises at least 15 mol% of at least one lanthanide sesquioxide and the balance comprising a first oxide selected from the group consisting of zirconia, ceria, and hafnia. Preferably the first oxide is present in an amount greater than 50 mol%. Each lanthanide sesquioxide has a formula A_2O_3 where A is selected from the group consisting of La, Pr, Nd, Sm, Eu, Tb, and mixtures thereof. In a preferred embodiment, the at least one lanthanide sesquioxide is present in a total amount in the range of 15 to 45 mol%. In a most preferred embodiment, the at least one lanthanide sesquioxide is present in a total amount of at least 25 mol%. In the thermal barrier coatings of the present invention, where the first oxide is zirconia, each zirconium ion has more than one adjacent oxide vacancy on average, and preferably at least two adjacent oxide vacancies. If the first oxide is hafnia or ceria, each hafnium ion and each cerium ion would also have more than one adjacent oxide vacancy on average, and preferably at least two adjacent oxide vacancies. The presence of these oxygen vacancies minimizes the thermal conductivity of the coating. Thus, they are a highly desirable feature of the coatings of the present invention.

[0028] A second thermal barrier coating in accordance with the present invention comprises an oxide present in an amount from 5 to 60 mol% and the balance comprising a first oxide selected from the group consisting of zirconia, hafnia, and ceria. The oxide has a formula A_2O_3 where A is selected from the group consisting of In, Sc, Y, Dy, Ho, Er, Tm, Yb, Lu, and mixtures thereof. In a preferred embodiment of this coating, the lanthanide sesquioxide is present in an amount from 10 to 40 mol%.

[0029] A third embodiment of a thermal barrier coating comprises a lanthanide sesquioxide and the balance comprising a first oxide selected from the group consisting of zirconia, hafnia, ceria, and mixtures thereof. The lanthanide sesquioxide is present in an amount sufficient to create more than one oxygen vacancy on average adjacent each zirconium, hafnium, and cerium ions.

[0030] A fourth embodiment of a thermal barrier coating having a lower thermal conductivity in accordance with the present invention comprises from 15 to 60 mol% of a lanthanide sesquioxide having a formula A_2O_3 where A is selected from the group consisting of Er, Nd, Yb, Eu, Dy, Pr, Sm, La, and mixtures thereof, and the balance zirconia. The thermal barrier coating preferably contains less than 10 vol% of phases with a pyrochlore crystal structure. Zirconia is preferably present in an amount greater than 40 mol%. The thermal barrier coating may also contain one or more of the following constituents: from 0.001 to 2.5 mol% yttria, from 0.001 to 10 mol% of at least one of CaO and MgO, from 0.001 to 1.0 mol% Yb_2O_3 , from 0.001 to 4.0 mol% Sc_2O_3 , and/or from 0.001 to 4.0 mol% In_2O_3 .

[0031] A fifth embodiment of a thermal barrier coating in accordance with the present invention which exhibits

a lower thermal conductivity comprises at least 15 mol% yttria, and a lanthanide sesquioxide having a formula A_2O_3 where A is selected from the group consisting of Er, Nd, Yb, Eu, Dy, Gd, Pr, and mixtures thereof, and the balance zirconia. In a preferred embodiment, the zirconia is present in an amount greater than 40 mol% and the coating contains less than 10 vol% of phases with a pyrochlore crystal structure. The yttria in this coating system may be present in an amount in the range of 15 to 22 mol% and the lanthanide sesquioxide may be present in an amount from 1.0 to 35 mol%. In a particularly useful embodiment of this thermal barrier coating system, yttria is present in an amount greater than 22 mol% and the lanthanide sesquioxide is present in an amount from 1.0 to 38 mol%.

[0032] In a sixth embodiment of the present invention, a thermal barrier coating having a lower thermal conductivity comprises from 9 to 15 mol% Yb_2O_3 , and from 1.0 to 48 mol% of a lanthanide sesquioxide having a formula A_2O_3 where A is selected from the group consisting of Er, Nd, Eu, Dy, Gd, Pr, and mixtures thereof, and the balance zirconia. The zirconia is present in an amount greater than 40 mol% and the coating has less than 10 vol% of a pyrochlore crystal structure.

[0033] A seventh embodiment of a thermal barrier coating in accordance with the present invention comprises greater than 15 mol% Yb_2O_3 and a lanthanide sesquioxide having a formula A_2O_3 where A is selected from the group consisting of Er, Nd, Eu, Dy, Gd, Pr, and mixtures thereof, and the balance zirconia. The zirconia is preferably present in an amount greater than 40 mol%. Further, the coating preferably contains less than 10 vol% of phases with a pyrochlore crystal structure. The lanthanide sesquioxide may be present in an amount from 0.001 to 45 mol%.

[0034] In an eighth embodiment of the present invention, a thermal barrier coating is provided which comprises from 20 to 30 mol% Sc_2O_3 and a lanthanide sesquioxide having a formula A_2O_3 where A is selected from the group consisting of Er, Nd, Eu, Dy, Gd, Pr, and mixtures thereof, and the balance zirconia. As before, the zirconia is preferably present in an amount greater than 40 mol%. Further, the thermal barrier coating has less than 10 vol% of phases with a pyrochlore crystal structure. In a preferred embodiment, the lanthanide sesquioxide is present in an amount from 0.001 to 30 mol%.

[0035] In a ninth embodiment of the present invention, a thermal barrier coating is provided which comprises greater than 30 mol% Sc_2O_3 , a lanthanide sesquioxide having a formula A_2O_3 where A is selected from the group consisting of Nd, Eu, Dy, Gd, Er, Pr, and mixtures thereof, and the balance zirconia. The zirconia is preferably present in an amount greater than 40 mol%. The thermal barrier coating may have less than 10 vol% of phases with a pyrochlore crystal structure. In a preferred embodiment, the lanthanide sesquioxide is present in an amount in the range of 0.001 to 30 mol%.

[0036] In a tenth embodiment of the present invention, a thermal barrier coating comprises from 11 to 20 mol% In_2O_3 and a lanthanide sesquioxide having a formula A_2O_3 where A is selected from the group consisting of Er, Nd, Eu, Dy, Gd, Pr, and mixtures thereof, and the balance zirconia. In a preferred embodiment, the lanthanide sesquioxide is present in an amount from 0.001 to 36 mol%. The zirconia is preferably present in an amount greater than 40 mol%. The coating also preferably contains less than 10 vol% of phases with a pyrochlore structure.

[0037] In an eleventh embodiment, a thermal barrier coating is provided which comprises more than 20 mol% In_2O_3 , and a lanthanide sesquioxide having a formula A_2O_3 where A is selected from the group consisting of Er, Nd, Eu, Dy, Gd, Pr, and mixtures thereof, and the balance zirconia. In this coating system, the zirconia is preferably present in an amount greater than 40 mol%, the lanthanide sesquioxide is preferably present in an amount from 0.001 to 40 mol%, and the coating contains less than 10 vol% of phases with a pyrochlore structure.

[0038] In a twelfth embodiment of the present invention, a thermal barrier coating comprises from 5 to 60 mol% of at least one of La_2O_3 and Sm_2O_3 , from 5 to 60 mol% of at least one oxide having the formula A_2O_3 where A is selected from the group consisting of Sc, In, Y, Pr, Nd, Eu, Sm, Gd, Dy, Er, Yb, and mixtures thereof, and the balance zirconia. In this coating system, the zirconia is preferably present in an amount greater than 40 mol% and the coating contains less than 10 vol% of phases with a pyrochlore structure.

[0039] Other embodiments of thermal barrier coatings in accordance with the present invention include the following.

[0040] (13) A thermal barrier coating comprising from 0.5 to 22.5 mol% of at least one first oxide having a formula A_2O_3 where A is selected from the group consisting of La, Sm, Tb, Tm, and Lu combined with a second oxide selected from the group consisting of zirconia, hafnia, and ceria. In a preferred embodiment, the second oxide is present in an amount of at least 77.5 mol%. The coating may also contain from 0.5 to 59.5 mol% of at least one third oxide from the group consisting of In_2O_3 , Sc_2O_3 , Y_2O_3 , MgO, CaO, and mixtures thereof with the second oxide being present in an amount greater than 40 mol% when the third oxide is present. Still further, the coating, in another variation, may contain from 0.5 to 22.0 mol% of at least one third oxide selected from the group consisting of CeO_2 , Pr_2O_3 , Nd_2O_3 , Eu_2O_3 , Gd_2O_3 , Dy_2O_3 , Er_2O_3 , Yb_2O_3 , and mixtures thereof, and the at least one first oxide and the at least one third oxide being present in a total content not greater than 22.5 mol%.

[0041] (14) A thermal barrier coating comprising from 0.5 to 1.0 mol% of at least one first oxide from the group consisting of CeO_2 , Pr_2O_3 , Nd_2O_3 , Eu_2O_3 , Gd_2O_3 , Dy_2O_3 , Er_2O_3 , Yb_2O_3 , In_2O_3 , Sc_2O_3 , Y_2O_3 , and mixtures thereof, combined with a second oxide selected

from the group consisting of zirconia, hafnia, and ceria. The thermal barrier coating may also contain from 0.5 to 22.0 mol% of at least one third oxide selected from the group consisting of La_2O_3 , Sm_2O_3 , Tb_2O_3 , Tm_2O_3 , Ho_2O_3 , Lu_2O_3 , MgO , CaO , and mixtures thereof, with the at least one first oxide and the at least one third oxide being present in a total amount of not greater than 22.5 mol%, and the second oxide being present in an amount of at least 77.5 mol%.

[0042] (15) A thermal barrier coating comprising from 20.5 to 22.5 mol% of CeO_2 combined with an oxide selected from the group consisting of zirconia, hafnia, and ceria. In a preferred embodiment, the oxide is present in an amount of at least 77.5 mol%.

[0043] (16) A thermal barrier coating comprising from 0.5 to 22.0 mol% of CeO_2 , and from 0.5 to 22.0 mol% of at least one first oxide selected from the group consisting of La_2O_3 , Sm_2O_3 , Tb_2O_3 , Tm_2O_3 , Ho_2O_3 , Lu_2O_3 , MgO , CaO , Pr_2O_3 , Nd_2O_3 , Eu_2O_3 , Gd_2O_3 , Dy_2O_3 , Er_2O_3 , Yb_2O_3 , and mixtures thereof, combined with a second oxide selected from the group consisting of zirconia and hafnia, and the CeO_2 and the at least one first oxide being present in an amount not greater than 22.5 mol%. In a preferred embodiment, the second oxide is present in an amount of at least 77.5 mol%.

[0044] (17) A thermal barrier coating comprising from 0.5 to 22.5 mol% CeO_2 , from 0.5 to 59.5 mol% of at least one oxide selected from the group consisting of In_2O_3 , Sc_2O_3 , and mixtures thereof, combined with at least 40 mol% of an oxide selected from the group consisting of zirconia and hafnia.

[0045] (18) A thermal barrier coating comprising from 9.0 to 22.5 mol% of at least one first oxide selected from the group consisting of Pr_2O_3 , Nd_2O_3 , Eu_2O_3 , Er_2O_3 , and mixtures thereof combined with a second oxide selected from the group consisting of zirconia, hafnia, and ceria. In a preferred embodiment, the second oxide is present in an amount greater than 77.5 mol%. The thermal barrier coating may further comprise from 0.5 to 51 mol% of at least one third oxide selected from the group consisting of Yb_2O_3 , In_2O_3 , Sc_2O_3 , Y_2O_3 , Gd_2O_3 , MgO , CaO , and mixtures thereof with the second oxide being present in an amount of at least 40 mol%.

[0046] (19) A thermal barrier coating comprising from 15.0 to 22.5 mol% of a first oxide selected from the group consisting of Dy_2O_3 and Yb_2O_3 combined with at least 77.5 mol% of a second oxide selected from the group consisting of zirconia, hafnia, and ceria.

[0047] (20) A thermal barrier coating comprising from 0.5 to 59.5 mol% of Dy_2O_3 and from 0.5 to 59.5 mol% of at least one oxide from the group consisting of In_2O_3 , Sc_2O_3 , MgO , CaO , and mixtures thereof, combined with at least 40 mol% of an oxide selected from the group consisting of zirconia, hafnia, and ceria.

[0048] (21) A thermal barrier coating comprising from 0.5 to 22.5 mol% of Yb_2O_3 , and from 0.5 to 59.5 mol% of at least one oxide from the group consisting of In_2O_3 , Sc_2O_3 , MgO , CaO , and mixtures thereof, combined with

at least 40 mol% of an oxide selected from the group consisting of zirconia, hafnia, and ceria.

[0049] (22) A thermal barrier coating comprising from 20.5 to 60 mol% of at least one oxide selected from the group consisting of In_2O_3 , Sc_2O_3 , and Y_2O_3 , combined with at least 40 mol% of an oxide selected from the group consisting of zirconia, hafnia, and ceria.

[0050] (23) A thermal barrier coating comprising from 15 to 59.5 mol% of Y_2O_3 , from 0.5 to 45 mol% of at least one first oxide selected from the group consisting of La_2O_3 , Sm_2O_3 , Tb_2O_3 , Tm_2O_3 , Ho_2O_3 , Lu_2O_3 , MgO , CaO , Pr_2O_3 , Nd_2O_3 , Eu_2O_3 , Dy_2O_3 , Er_2O_3 , Yb_2O_3 , In_2O_3 , Sc_2O_3 , and mixtures thereof, combined with at least 40 mol% of an oxide selected from the group consisting of zirconia, hafnia, and ceria.

[0051] (24) A thermal barrier coating comprising from 9.0 to 23.0 mol% Gd_2O_3 , from 0.5 to 51.0 mol% of at least one first oxide selected from the group consisting of La_2O_3 , Sm_2O_3 , Tb_2O_3 , Tm_2O_3 , Ho_2O_3 , Lu_2O_3 , MgO , CaO , Pr_2O_3 , Nd_2O_3 , Eu_2O_3 , Dy_2O_3 , Er_2O_3 , Yb_2O_3 , In_2O_3 , Sc_2O_3 , and mixtures thereof, combined with at least 40 mol% of an oxide selected from the group consisting of zirconia, hafnia, and ceria.

[0052] The various thermal barrier coatings set forth herein may be characterized with a columnar structure.

[0053] An article, having particular utility as a component in a gas turbine engine, may be provided in accordance with the present invention. The article may have a metal substrate and one of the aforementioned thermal barrier coatings applied to the substrate. The thermal barrier coating may be applied directly to a surface of the substrate or may be applied to a bond coat deposited on one or more surfaces of the metal substrate. Any suitable technique known in the art may be used to deposit a thermal barrier coating in accordance with one of the embodiments of the present invention. Suitable techniques include electron beam physical vapor deposition, chemical vapor deposition, LPPS techniques, and diffusion processes. The metal substrate may comprise one of a nickel based superalloy, a cobalt based superalloy, a ferrous alloy such as steel, a titanium alloy, and a copper alloy.

[0054] The bond coat may comprise any suitable bond coat known in the art. For example, the bond coat may be formed from an aluminum containing material, an aluminide, a platinum aluminide, a ceramic material, such as 7wt% yttria stabilized zirconia, or a MCrAlY material. The bond coat may be formed on the substrate using any suitable process known in the art including, but not limited to, low pressure plasma spray, electron beam physical vapor deposition, diffusion processes and chemical vapor deposition processes. If desired, the bond coat may have an oxide scale on an outer surface, which oxide scale consists essentially of alumina. The thermal barrier coatings of the present invention may be bonded to the oxide scale using any suitable technique known in the art.

[0055] If desired, a ceramic layer may be bonded to

the thermal barrier coating. The additional ceramic material may be selected from the group consisting of materials which reduce oxygen diffusion, provide erosion and abrasion resistance, and/or provide optical emissivity of 0.7. Examples of high emissivity ceramic materials which can be used are alumina and mullite. High emissivity reduces the heat transfer across a thermal barrier coating by internal radiation (radiation of the thermal barrier coating material itself) due to the temperature difference between the hotter outer surface of the coating and the cooler interface between the coating and the TGO, thereby reducing the temperature of the TGO, thus the bondcoat, thus the alloy. Thus, high emissivity increases the insulative properties of the TBC. The additional ceramic layer may be formed over an exterior surface of the thermal barrier coating.

[0056] In some embodiments, the article may have an oxide scale on its surfaces and one of the thermal barrier coatings of the present invention may be applied directly over and bonded to the oxide scale using any suitable deposition technique known in the art including, but not limited to, diffusion processes, electron beam physical vapor deposition, and/or chemical vapor deposition techniques. The oxide scale may consist substantially of alumina.

[0057] Although the thermal barrier coatings of the present invention were developed for application in gas turbine engines, the coatings have utility in other applications where high temperatures are encountered, such as furnaces and internal combustion engines.

[0058] The following examples are intended to show the advantages of the coatings of the present invention.

EXAMPLE 1

[0059] Samples of 27.3 mole% Y_2O_3 , balance ZrO_2 , were produced by cold pressing and sintering of mixed powders to a density 95% of theoretical. The sample discs, 0.025" in thickness, were coated with graphite. Specific heat and thermal diffusivity measurements were made using the laser flash apparatus. Bulk density was determined by careful measurement of the sample dimensions and weight. Thermal conductivity values of 1.95 W/mK were calculated from the data measured at 1200°F, linearly corrected to theoretical density.

EXAMPLE 2

[0060] Samples of 16.7 mole% Y_2O_3 , 16.7 mole% Gd_2O_3 , balance ZrO_2 , were similarly produced by cold pressing and sintering of mixed powders to a density 90.8% of theoretical. The 0.025"-thick samples were again coated with graphite and measured in the laser flash apparatus. From careful measurements of sample weight and dimensions, the bulk density of the sample was determined. Thermal conductivity values averaging 1.37 W/mK were calculated from the data measured at 1600°F, linearly corrected to theoretical density.

EXAMPLE 3

[0061] Coatings with an average composition of 19 mole% Sm_2O_3 , balance ZrO_2 , were deposited by electron beam physical vapor deposition onto alumina discs. High temperature measurements of thermal diffusivity were made in the laser flash apparatus. High temperature specific heat values were estimated from previous measurements of monolithic 33 mole% Sm_2O_3 , balance ZrO_2 samples. Bulk density of the samples was calculated from the changes in weight and thickness of the discs during coating, and their diameters. Thermal conductivity values averaging 1.26 W/mK were calculated from the data measured at 1400°F, with no correction made for density.

Claims

1. A thermal barrier coating comprising at least 15 mol% of at least one lanthanide sesquioxide, each said lanthanide sesquioxide having a formula A_2O_3 where A is selected from the group consisting of La, Pr, Nd, Sm, Eu, Tb, and mixtures thereof, and the balance comprising a first oxide selected from the group consisting of zirconia, ceria, and hafnia, said first oxide being present in an amount of at least 50 mol%.
2. A thermal barrier coating according to claim 1, wherein said at least one lanthanide sesquioxide is present in a total amount in the range of 15 - 45 mol%.
3. A thermal barrier coating according to claim 1 or 2, wherein said at least one lanthanide sesquioxide is present in a total amount of at least 25 mol%.
4. A thermal barrier coating according to claim 1, 2 or 3, wherein said first oxide is zirconia.
5. A thermal barrier coating according to claim 1, 2 or 3, wherein said first oxide is hafnia.
6. A thermal barrier coating according to claim 1, 2 or 3, wherein said first oxide is ceria.
7. A thermal barrier coating comprising from 0.5 to 22.5 mol% of at least one first oxide having a formula A_2O_3 where A is selected from the group consisting of La, Sm, Tb, Tm, and Lu combined with a second oxide selected from the group consisting of zirconia, hafnia, and ceria.
8. A thermal barrier coating according to claim 7, wherein said second oxide is present in an amount of at least 77.5 mol%.

9. A thermal barrier coating according to claim 7, further comprising from 0.5 to 59.5 mol% of at least one oxide from the group consisting of In_2O_3 , Sc_2O_3 , Y_2O_3 , MgO , CaO , and mixtures thereof and said second oxide being present in an amount greater than 40 mol%. 5
10. A thermal barrier according to claim 7, further comprising from 0.5 to 22.0 mol% of at least one third oxide selected from the group consisting of CeO_2 , Pr_2O_3 , Nd_2O_3 , Eu_2O_3 , Gd_2O_3 , Dy_2O_3 , Er_2O_3 , Yb_2O_3 , and mixtures thereof, and said at least one first oxide and said at least one third oxide being present in a total content not greater than 22.5 mol%. 10
11. A thermal barrier coating comprising from 0.5 to 1.0 mol% of at least one first oxide from the group consisting of CeO_2 , Pr_2O_3 , Nd_2O_3 , Eu_2O_3 , Gd_2O_3 , Dy_2O_3 , Er_2O_3 , Yb_2O_3 , In_2O_3 , Sc_2O_3 , Y_2O_3 , and mixtures thereof, combined with a second oxide selected from the group consisting of zirconia, hafnia, and ceria. 20
12. A thermal barrier coating according to claim 11, further comprising from 0.5 to 22.5 mol% of at least one third oxide selected from the group consisting of La_2O_3 , Sm_2O_3 , Tb_2O_3 , Tm_2O_3 , Ho_2O_3 , Lu_2O_3 , MgO , CaO , and mixtures thereof, said at least one first oxide and said at least one third oxide being present in a total amount of not greater than 22.5 mol%, and said second oxide being present in an amount of at least 77.5 mol%. 25
13. A thermal barrier coating comprising from 20.5 to 22.5 mol% of CeO_2 combined with an oxide selected from the group consisting of zirconia, hafnia, and ceria. 30
14. A thermal barrier coating according to claim 13, wherein said oxide is present in an amount of at least 77.5 mol%. 35
15. A thermal barrier coating comprising from 0.5 to 22.0 mol% of CeO_2 , and from 0.5 to 22.0 mol% of at least one first oxide selected from the group consisting of La_2O_3 , Sm_2O_3 , Tb_2O_3 , Tm_2O_3 , Ho_2O_3 , Lu_2O_3 , MgO , CaO , Pr_2O_3 , Nd_2O_3 , Eu_2O_3 , Gd_2O_3 , Dy_2O_3 , Er_2O_3 , Yb_2O_3 , and mixtures thereof, combined with a second oxide selected from the group consisting of zirconia and hafnia, and said CeO_2 and said at least one first oxide being present in an amount not greater than 22.5 mol%. 40
16. A thermal barrier coating according to claim 15, wherein said second oxide is present in an amount of at least 77.5 mol%. 45
17. A thermal barrier coating comprising from 0.5 to 22.5 mol% CeO_2 , from 0.5 to 59.5 mol% of at least one oxide selected from the group consisting of In_2O_3 , Sc_2O_3 , and mixtures thereof, combined with at least 40 mol% of an oxide selected from the group consisting of zirconia and hafnia. 50
18. A thermal barrier coating comprising from 9.0 to 22.5 mol% of at least one first oxide selected from the group consisting of Pr_2O_3 , Nd_2O_3 , Eu_2O_3 , Er_2O_3 , and mixtures thereof combined with a second oxide selected from the group consisting of zirconia, hafnia, and ceria. 55
19. A thermal barrier coating according to claim 18, wherein said second oxide is present in an amount greater than 77.5 mol%.
20. A thermal barrier coating according to claim 18, further comprising from 0.5 to 51.0 mol% of at least one third oxide selected from the group consisting of Yb_2O_3 , In_2O_3 , Sc_2O_3 , Y_2O_3 , Gd_2O_3 , MgO , CaO , and mixtures thereof and said second oxide being present in an amount of at least 40 mol%.
21. A thermal barrier coating comprising from 15.0 to 22.5 mol% of a first oxide selected from the group consisting of Dy_2O_3 and Yb_2O_3 combined with at least 77.5 mol% of a second oxide selected from the group consisting of zirconia, hafnia, and ceria.
22. A thermal barrier coating comprising from 0.5 to 59.5 mol% of Dy_2O_3 and from 0.5 to 59.5 mol% of at least one oxide from the group consisting of In_2O_3 , Sc_2O_3 , MgO , CaO , and mixtures thereof, combined with at least 40 mol% of an oxide selected from the group consisting of zirconia, hafnia, and ceria.
23. A thermal barrier coating comprising from 0.5 to 22.5 mol% of Yb_2O_3 , and from 0.5 to 59.5 mol% of at least one oxide from the group consisting of In_2O_3 , Sc_2O_3 , MgO , CaO , and mixtures thereof, combined with at least 40 mol% of an oxide selected from the group consisting of zirconia, hafnia, and ceria.
24. A thermal barrier coating comprising from 20.5 to 60 mol% of at least one oxide selected from the group consisting of In_2O_3 , Sc_2O_3 , and Y_2O_3 , combined with at least 40 mol% of an oxide selected from the group consisting of zirconia, hafnia, and ceria.
25. A thermal barrier coating comprising from 15 to 59.5 mol% of Y_2O_3 , from 0.5 to 45.0 mol% of at least one first oxide selected from the group consisting of La_2O_3 , Sm_2O_3 , Tb_2O_3 , Tm_2O_3 , Ho_2O_3 , Lu_2O_3 , 55

- MgO, CaO, Pr_2O_3 , Nd_2O_3 , Eu_2O_3 , Dy_2O_3 , Er_2O_3 , Yb_2O_3 , In_2O_3 , Sc_2O_3 , and mixtures thereof, combined with at least 40 mol% of an oxide selected from the group consisting of zirconia, hafnia, and ceria.
26. A thermal barrier coating comprising from 9.0 to 23 mol% Gd_2O_3 , from 0.5 to 51.0 mol% of at least one first oxide selected from the group consisting of La_2O_3 , Sm_2O_3 , Tb_2O_3 , Tm_2O_3 , Ho_2O_3 , Lu_2O_3 , MgO , CaO , Pr_2O_3 , Nd_2O_3 , Eu_2O_3 , Dy_2O_3 , Er_2O_3 , Yb_2O_3 , In_2O_3 , Sc_2O_3 , and mixtures thereof, combined with at least 40 mol% of an oxide selected from the group consisting of zirconia, hafnia, and ceria.
27. A thermal barrier coating comprising greater than 30 mol% Sc_2O_3 , a lanthanide sesquioxide having a formula A_2O_3 where A is selected from the group consisting of Nd, Eu, Dy, Gd, Er, Pr, and mixtures thereof, and the balance zirconia.
28. A thermal barrier coating according to claim 27, wherein said zirconia is present in an amount greater than 40 mol%.
29. A thermal barrier coating according to claim 27 or 28, wherein said coating has less than 10 vol% of phases with a pyrochlore crystal structure.
30. A thermal barrier coating according to claim 27, wherein said lanthanide sesquioxide is present in an amount in the range of 0.001 to 30 mol%.
31. A thermal barrier coating comprising more than 20 mol% In_2O_3 , and a lanthanide sesquioxide having a formula A_2O_3 where A is selected from the group consisting of Er, Nd, Eu, Dy, Gd, Pr, and mixtures thereof, and the balance zirconia.
32. A thermal barrier coating according to claim 31, wherein said zirconia is present in an amount greater than 40 mol%.
33. A thermal barrier coating according to claim 31 or 32, wherein said coating contains less than 10 vol% of phases with a pyrochlore crystal structure.
34. A thermal barrier coating according to claim 31, wherein said lanthanide sesquioxide is present in an amount from 0.001 to 40 mol%.
35. A thermal barrier coating comprising from 5 to 60 mol% of at least one of La_2O_3 and Sm_2O_3 , and from 5 to 60 mol% of at least one oxide having a formula A_2O_3 where A is selected from the group consisting of Sc, In, Y, Pr, Nd, Eu, Sm, Gd, Dy, Er, Yb, and mixtures thereof, and the balance zirconia.
36. A thermal barrier coating according to claim 35, wherein said zirconia is present in an amount greater than 40 mol%.
37. A thermal barrier coating according to claim 35 or 36, wherein said coating contains less than 10 vol% of phases with a pyrochlore crystal structure.
38. A thermal barrier coating as claimed in any one of the preceding claims, wherein said thermal barrier coating has a columnar structure.
39. An article having a metal substrate and a thermal barrier coating as claimed in any one of the preceding claims.
40. An article according to claim 39, wherein said metal substrate comprises at least one of a nickel based superalloy, a cobalt based superalloy, a ferrous alloy, a titanium alloy, and a copper alloy.
41. An article according to claim 39 or 40, further comprising a bond coat intermediate said metal substrate and said thermal barrier coating.
42. An article according to claim 41, wherein said bond coat is formed from at least one of an aluminum containing material, an aluminide, a platinum aluminide, a MCrAlY material, and yttria stabilized zirconia.
43. An article according to any of claims 39 to 42, wherein said article comprises a component used on a turbine engine or an internal combustion engine.
44. An article according to claim 39, wherein the metallic substrate has an oxide scale on an outer surface consisting substantially of alumina, and the thermal barrier coating is bonded to the oxide scale.
45. An article according to claim 41 or 42, wherein the bond coat has an oxide scale on its outer surface and the thermal barrier coating is bonded to the oxide scale on the outer surface.
46. An article according to claim 39, further comprising a ceramic bond coat between the thermal barrier coating and the metallic substrate.
47. An article according to any of claims 41 to 46, further comprising an additional ceramic layer on said thermal barrier coating, and said additional ceramic layer being formed from a material selected from the group consisting of materials which reduce oxygen diffusion, provide erosion and abrasion resistance, and/or have a level of optical emissivity of 0.7.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 03 25 5192

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	EP 0 812 931 A (TOSOH CORP) 17 December 1997 (1997-12-17) * see p.3, lines 13-17 * * the whole document *	1-47	C23C30/00 C23C16/00 C23C14/22 C23C14/08
X	EP 0 595 451 A (PRAXAIR TECHNOLOGY INC) 4 May 1994 (1994-05-04) * see p.2, lines 32 -41, claims 1 and 2 * * the whole document *	1-47	
Y	WO 99 42630 A (GADOW RAINER ;SCHAEFER GUENTER WILHELM (DE)) 26 August 1999 (1999-08-26) * see p.4, l.10-18, claims * * the whole document *	1-47	
Y	EP 0 825 271 A (ROLLS ROYCE PLC) 25 February 1998 (1998-02-25) * see p.4, col5, line 28-35, claims * * the whole document *	1-47	
Y	US 4 774 150 A (TAKAHASHI YOSHIKAZU ET AL) 27 September 1988 (1988-09-27) * see col.2, line 25-41, claims * * the whole document *	1-47	TECHNICAL FIELDS SEARCHED (Int.Cl.7) C23C
Y	US 6 333 090 B1 (KROEDER CLAUS-JUERGEN ET AL) 25 December 2001 (2001-12-25) * see col. 7, lines 28-33, claims 1, 4, 5 and 10 * * the whole document *	1-47	
Y	WO 02 14580 A (SIEMENS WESTINGHOUSE POWER) 21 February 2002 (2002-02-21) * see claims * * the whole document *	1-47	
		-/--	
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 22 January 2004	Examiner Stellmach, J
CATEGORY OF CITED DOCUMENTS		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document			

EPO FORM 1503 03 82 (P04C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 03 25 5192

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
Y	WO 97 01436 A (GEN ELECTRIC) 16 January 1997 (1997-01-16) * see claims * * the whole document *	1-47	
P,Y	EP 1 249 515 A (GEN ELECTRIC) 16 October 2002 (2002-10-16) * see p.3, 1.15-18, claim 2 * * the whole document *	1-47	
P,Y	EP 1 295 965 A (GEN ELECTRIC) 26 March 2003 (2003-03-26) * see claims 1 and 9 * * the whole document *	1-47	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 22 January 2004	Examiner Stellmach, J
CATEGORY OF CITED DOCUMENTS		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document			

EPO FORM 1503 03.82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 03 25 5192

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

22-01-2004

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
EP 0812931	A	17-12-1997	DE	69700448 D1	30-09-1999
			DE	69700448 T2	13-01-2000
			EP	0812931 A1	17-12-1997
			JP	10081957 A	31-03-1998
			US	5789330 A	04-08-1998

EP 0595451	A	04-05-1994	US	5304519 A	19-04-1994
			CA	2094531 A1	29-04-1994
			CN	1086234 A ,B	04-05-1994
			DE	69302252 D1	23-05-1996
			DE	69302252 T2	19-09-1996
			EP	0595451 A1	04-05-1994
			JP	2824189 B2	11-11-1998
			JP	6135768 A	17-05-1994
			KR	136554 B1	25-04-1998
			US	5466208 A	14-11-1995
			US	5418015 A	23-05-1995

WO 9942630	A	26-08-1999	DE	19807163 C1	28-10-1999
			AT	218626 T	15-06-2002
			DE	59901628 D1	11-07-2002
			WO	9942630 A1	26-08-1999
			EP	1060281 A1	20-12-2000
			ES	2177251 T3	01-12-2002
			JP	2002504627 T	12-02-2002
			PT	1060281 T	31-10-2002
			US	6602814 B1	05-08-2003

EP 0825271	A	25-02-1998	DE	69713001 D1	11-07-2002
			DE	69713001 T2	27-02-2003
			EP	0825271 A1	25-02-1998
			US	6025078 A	15-02-2000

US 4774150	A	27-09-1988	JP	62207885 A	12-09-1987

US 6333090	B1	25-12-2001	NONE		

WO 0214580	A	21-02-2002	US	6258467 B1	10-07-2001
			CA	2417212 A1	21-02-2002
			EP	1309738 A2	14-05-2003
			WO	0214580 A2	21-02-2002
			US	2002061416 A1	23-05-2002

WO 9701436	A	16-01-1997	CH	690582 A5	31-10-2000
			DE	19680503 T0	08-01-1998
			IN	187269 A1	16-03-2002

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 03 25 5192

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

22-01-2004

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9701436	A		JP 10505299 T	26-05-1998
			WO 9701436 A1	16-01-1997
			US 5914189 A	22-06-1999

EP 1249515	A	16-10-2002	US 2002172838 A1	21-11-2002
			BR 0201230 A	31-12-2002
			EP 1249515 A2	16-10-2002

EP 1295965	A	26-03-2003	US 2003059633 A1	27-03-2003
			EP 1295965 A2	26-03-2003

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82